



SUNMARK



VINYL
POLYURETHANE*
*(4114 / 4107)



100°C



PEEL : COLD



Flex Blade 45°
Medium Pressure



90 - 160 µm



15 Sec

SPECIFICATIONS

APPLICATION

1. Cut the material in reverse with a Flex regular blade
2. Weed the excess material
3. Heat press on a SEFA machine on the garment at 100° C & Protect the polyester carrier with silicone paper
15 sec - medium pressure
4. Peel the carrier off when cold

THICKNESS:  Vinyl / Polyurethane 90- 160 microns

CARRIER: Adhesive & Transparent polyester



APPLIES ON

Awings and heat sensitive fabrics

CARE & MAINTENANCE

- Always respect the garment's instructions
- Allow 24 hours after application before washing
- Iron the backside only

WASH

- Do not wash

STORE

- Up to 1 year
- In a dry room (15-30° C)
- Away from sunlight
- In vertical position

Chemica
Heat transfers for textiles